

Wipes soaked by pickling solution for stainless steel

- Especially suitable for pickling TIG / MIG / electrode austenitic stainless steel welds.
- Ready to use.



SURFACE PROTECTION AND TREATMENT

Svar-X

GENERAL INFORMATION

SVA

SVAR-X is a wipe soaked in pickling solution for stainless steel specification. It is ready to use. SVAR-X is especially suitable for pickling TIG / MIG / electrode austenitic stainless steel welds. After use, the clean area should be treated with the SVAR-X CLEANER, in order to neutralize and remove product residue.

TECHNICAL INFORMATION

Color: colorless Odor: strong Physical state: wipe soaked liquid pH of liquid solution: 1 Storage: Keep the product in a safe place and in the original container.

APPLICATION AND USE

- Apply the wipe along the weld, ensuring it adheres to the surface.Leave on for at least 10/15 minutes (depends of outside temperature and the quality of the weld).
- Remove the Svar-X wipe. Spray SVAR-X CLEANER on the worked surface to neutralize the acid residues.

a duration of 4 months.


Once the package is opened the wipes have

Do not mix it with other products.

Shelf life: 2 years

 Dry with blotting paper and close the SVAR-X wipe blister with the cover.

Article nr	Name	Content	Section
X134001	Svar-X 25m x 4cm	1 pc.	SURFACE PROTECTION AND TREATMENT
X134002	Svar-X Cleaner	1L	SURFACE PROTECTION AND TREATMENT









All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Xintex is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Xintex products provide, relates only to the standard conditions of sale of this product. In no case Xintex can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.

TECH-MASTERS TRADING GMBH

Perfektastraße 55, 1230 Wien, Austria, Tel +43 (0) 1 / 867 29 07 Fax +43 (0) 1 / 867 29 93, E-Mail office@tech-masters-trading.com



